



Autoxtreme

One Hardener, Many Products.

Autokote Systems' line of Autoxtreme Hardeners – **Fast, Medium, Slow, and X-Slow** – all work with the line of Autoxtreme Clearcoats and Single-Stage products. Simplify your daily mixing process.



HARDENERS

PART NO.	DESCRIPTION	UOM
AK.6654	Autoxtreme Fast Hardener	Quart
AK.6659	Autoxtreme Fast Hardener	Half Pint
AK.6754	Autoxtreme Medium Hardener	Quart
AK.6759	Autoxtreme Medium Hardener	Half Pint
AK.6854	Autoxtreme Slow Hardener	Quart
AK.6759	Autoxtreme Slow Hardener	Half Pint
AK.6954	Autoxtreme X-Slow Hardener	Quart

SINGLE-STAGE

PART NO.	DESCRIPTION	UOM
AK.6001	Autoxtreme SB Satin Black	Gallon
AK.6004	Autoxtreme SB Satin Black	Quart
AK.6011	Gloss Black Urethane	Gallon

CLEARCOATS

PART NO.	DESCRIPTION	UOM
AK.6101	Autoxtreme HD Clearcoat	Gallon
AK.6201	Autoxtreme XP Clearcoat	Gallon
AK.6204	Autoxtreme XP Clearcoat	Quart
AK.6401	Autoxtreme AD Clearcoat	Gallon
AK.6501	Autoxtreme MS Clearcoat	Gallon
AK.6304	Autoxtreme LG Clearcoat	Quart



Autotreme HD Clearcoat is an extreme high definition clearcoat with excellent leveling characteristics, formulated to perform equally well in baking or air-dry environments.

- ▼ 2:1 Mix Ratio
- ▼ 2 Full Wet Coats
- ▼ 5-10 Minutes Flash
- ▼ Dust-free 20-30 Minutes @ 75°F
- ▼ Tack-free 2 Hours @ 75°F
- ▼ 8 hours Air Dry @ 75°F
- ▼ 40 Minutes Force Dry @ 140°F

Autotreme XP Clearcoat has been specifically formulated for the mobile repair industry. Autotreme XP Clearcoat is a 2K acrylic urethane clear with superior UV and chemical resistance properties and offers a fantastic high-gloss appearance.

- ▼ 3:1 Mix Ratio
- ▼ 2 Full Wet Coats
- ▼ 1-5 Minutes Flash
- ▼ Dust-free 5-10 Minutes @ 75°F
- ▼ Tack-free 15-20 Minutes @ 75°F
- ▼ 1.5-3 Hours Air Dry @ 75°F
- ▼ 30 Minutes Force Dry @ 140°F

Autotreme AD Clearcoat is the fastest air-dry/express bake clear offered. It also revolutionizes energy savings and productivity without sacrificing appearance. This 4.2 V.O.C. 2-component clearcoat can be used for spot and multi-panel repairs. Perfect for exterior panels, underside of hoods, engine compartment, trunk lids and backside of body panels.

- ▼ 4:1 Mix Ratio
- ▼ 2-4 Full Wet Coats
- ▼ 1-2 Minutes Flash
- ▼ Dust-free 2 Minutes @ 75°F
- ▼ Tack-free 5 Minutes @ 75°F
- ▼ 30-45 Minutes Air Dry @ 75°F
- ▼ 5-8 Minutes Force Dry @ 120°F-140°F

Autotreme MS Clearcoat is a high-quality acrylic urethane clear designed for multi-panel and overall applications. Autotreme MS Clearcoat contains European resins which provide a high-gloss, long-lasting finish, and chemical resistance properties.

- ▼ 4:1 Mix Ratio
- ▼ 2 Full Wet Coats
- ▼ 10-15 Minutes Flash
- ▼ Dust-free 10-12 Minutes @ 75°F
- ▼ Tack-free 30-40 Minutes @ 75°F
- ▼ 8 Hours Air Dry @ 75°F
- ▼ 20-40 Minutes Force Dry @ 140°F